

## BUDERUS CORROSION-RESISTANT KNIFE STEEL 4034 X46Cr13

	C	Si	Mn	P	S	Cr
Typical analysis	0.45	0.35	0.30	0,020	0.001	13.00
Chemical composition as per DIN EN 10088	0.43 - 0.50	≤ 1.00	≤ 1.00	≤ 0.040	≤ 0.015	12.50 - 14.50


Values in weight %

### HEAT TREATMENT


Soft annealing	750 °C - 840 °C (furnace)	1,380 °F - 1,544 °F (furnace)
Hardening	980 °C - 1,030 °C (oil)	1,795 °F - 1,885 °F (oil)
Tempering	see tempering curve	

### PHYSICAL PROPERTIES (REFERENCE VALUES FOR 20 °C / 68 °F)

Density [g/cm <sup>3</sup> ]	7.7
Young's modulus [GPa]	220
Thermal expansion [10 <sup>-6</sup> /K]	10.2
Thermal conductivity [W/m*K]	24.6
Electrical resistance [Ω * mm <sup>2</sup> /m]	0.58



TTT CURVE (CONTINUOUS)



TEMPERING CURVE

Legal notice: Buderus Edelstahl GmbH has taken every possible care in compiling this information; the data is nevertheless subject to intervening changes. Buderus Edelstahl GmbH disclaims all liability and any warranty as regards the accuracy, currency, correctness and completeness of the information provided. The information provided is merely descriptive and indicative in nature, and binding only when expressly agreed as undertakings in a contract made with Buderus Edelstahl GmbH. Buderus Edelstahl GmbH moreover reserves the right to make changes at any time without prior notice. Buderus Edelstahl GmbH disclaims all liability for loss or damage of any kind, including consequential loss, arising in connection with use of the information provided. This publication supersedes all previous ones.  
© Buderus Edelstahl GmbH, Wetzlar, 09/2015