

Buderus Plastic Mould Steel Thruhard Supreme® 2738mod.TS(HHH)

	C	Si	Mn	P	S	Cr	Ni	Mo	V
Typical analysis	0.26	0.10	1.45	0.015	0.002	1.25	1.05	0.70	0.15

Figures in % by mass

Its higher hardness compared to 2738mod.TS(HH) is achieved by its optimised chemical composition.

Characteristics

Both plastic mould steel variants of Thruhard Supreme® distinguished from grades 2311 and 2738 by:

- | Higher hardness and better through-hardening ability
- | Polishability up to 600 grit
- | Grain reliability even with sensitive etch-graining designs
- | Improved weldability
- | Higher thermal conductivity.

Nitridable, hard chrome plateable, flame hardenable as delivered; its higher basic hardness provides better support for surface finishing (such as PVD coating).

For high gloss polish requirements we recommend Thruhard Diamond®.

Applications

Compression and injection moulds to accommodate large dimensions such as bumpers, dashboards, chairs, rubbish bins, bottle crates, television cabinets, etc.

Delivered condition

- | TripleHard: 2738mod.TS(HHH)
Quenched and tempered to 355–400 HB (Δ approx. 1200–1350 MPa)*

Physical properties (reference values)

Thermal expansion coefficient ($10^{-6}/K$)	20–100 °C	20–250 °C	20–500 °C
	10.8	12.2	13.9
Thermal conductivity (W/mK)	20 °C	250 °C	500 °C
	37.4	41.3	39.8
Young's modulus (GPa)	20 °C	250 °C	500 °C
	204	188	160


* Surface hardness in Brinell, converted to DIN EN ISO 18265, Table A.1




Thruhard Supreme® 2738mod.TS(HHH)

Heat treatment	
Stress relieving	Temperature: Approx. 520 °C in the quenched and tempered state Duration: 1 hour per 50 mm wall thickness Cooling: Furnace
Soft annealing	Temperature: 720 °C Duration: 1 hour per 25 mm wall thickness Cooling: Furnace
Hardening	Temperature: 880 °C Duration: 1 minute per mm wall thickness
Quenching hardness	Max. 51 HRC in water, polymer, oil or vacuum
Tempering	Temperature: See tempering curve Duration: 1 hour per 25 mm wall thickness Cooling: Air
Working hardness	340–400 HB


Tempering curve



TTT curve (continuous)



Through-hardenability (schematic)



Legal notice: Buderus Edelstahl GmbH has taken every possible care in compiling this information; the data is nevertheless subject to intervening changes. Buderus Edelstahl GmbH disclaims all liability and any warranty as regards the accuracy, currency, correctness and completeness of the information provided. The information provided is merely descriptive and indicative in nature, and binding only when expressly agreed as undertakings in a contract made with Buderus Edelstahl GmbH. Buderus Edelstahl GmbH moreover reserves the right to make changes at any time without prior notice. Buderus Edelstahl GmbH disclaims all liability for loss or damage of any kind, including consequential loss, arising in connection with use of the information provided. This publication supersedes all previous ones.
© Buderus Edelstahl GmbH, Wetzlar, 06/2014